

# Curing Concrete

Curing is defined as **“maintenance of a satisfactory moisture content and temperature in the concrete for a period of time immediately following placing and finishing so that the desired properties may develop.”** Early curing is critical when the concrete will be exposed to harsh Canadian weather conditions since it dramatically affects the permeability and durability of the concrete. In some instances curing must be initiated even before the finishing operations are complete to provide the necessary concrete properties.

Since the strength and durability properties of concrete are set by the chemical reactions of the various components during the hydration process, there are three key factors to proper curing.

- **Moisture** – Having sufficient moisture to ensure the hydration process continues
- **Temperature** – Maintaining a sufficient temperature ( $\geq 10^{\circ}\text{C}$ ) to ensure that the chemical reaction continues
- **Time** – Maintaining both the moisture and temperature requirements for a minimum period of time (3 – 7 days – See CSA A23.1 – Table 20) to ensure that the durability properties fully develop. Curing needs to be initiated as soon as the finishing operations are complete and the surface will not be damaged by the curing operation.



Photo courtesy of CAC

## General Notes Regarding Concrete Curing:

1. Alternating cycles of wetting and drying during the curing process is extremely harmful to the concrete surface and may result in surface crazing and cracking. **This should be avoided at all costs.**
2. A 28 day air drying period is recommended immediately following the 28 day curing period to provide the necessary freeze/thaw resistance for the concrete. Curing methods that result in fully saturated concrete, which will be exposed to freeze/thaw cycles once the curing period is over, may result in premature deterioration of the concrete (even if the concrete is properly air entrained).
3. Concrete with low W/CM ratios ( $\leq 0.40$ ) may not have sufficient free moisture in the mix to allow for the use of **“moisture loss prevention”** curing methods. This situation should be reviewed prior to the start of the project.

Curing of concrete can be completed by two basic methods:

- Preventing the loss of moisture from the concrete
- Keeping the exposed surface continuously wet



Photo courtesy of RMCAO



Possible curing methods are outlined in the following table:

Moisture Loss Prevention	Supplying Supplemental Moisture
<ul style="list-style-type: none"> <li>■ <b>Curing Compounds</b> <ul style="list-style-type: none"> <li>Form a membrane over the top surface of the concrete preventing moisture loss</li> <li>Must be applied at the manufacturers suggested application rate</li> <li>Should be applied in two applications with the second being at right angles to the first to ensure uniform coverage</li> <li>Should be applied as soon as the concrete surface is finished and when there is no free water on the surface</li> <li>Curing compounds can effect the “bond” of some floor coverings</li> <li>Confirm that this curing method is suitable for the final floor covering application</li> </ul> </li> </ul>	<ul style="list-style-type: none"> <li>■ <b>Water Ponding</b> <ul style="list-style-type: none"> <li>Flooding of the concrete surface to provide both moisture and a uniform curing temperature</li> <li>Curing water should not be more than 12°C cooler than the concrete temperature to avoid the possibility of thermal cracking</li> <li>The water must cover the entire concrete surface</li> </ul> </li> </ul>
<ul style="list-style-type: none"> <li>■ <b>Plastic Sheeting</b> <ul style="list-style-type: none"> <li>Ensure that the plastic sheeting covers 100% of the concrete surface and that it is adequately sealed at the edges to prevent moisture loss</li> <li>Select the appropriate colour (white, black, or clear) of the plastic based upon the ambient air conditions</li> <li>If uniform colour is a requirement for the project ensure that the plastic is not placed directly on the concrete surface</li> <li>Ensure that plastic sheeting is not damaged by subsequent construction activities during the curing period</li> </ul> </li> </ul>	<ul style="list-style-type: none"> <li>■ <b>Water Sprinkling</b> <ul style="list-style-type: none"> <li>Spraying water over the concrete surface. The entire concrete surface must be wet for this method to be effective</li> <li>The concrete surface must have sufficient strength to avoid damaging the surface</li> <li>Excess water will run off the concrete and must be drained away</li> <li>This protection method can be adversely affected by high winds which prevent proper curing on the “upwind” side</li> </ul> </li> </ul>
<ul style="list-style-type: none"> <li>■ <b>Leaving Formwork In Place</b> <ul style="list-style-type: none"> <li>This system is most effective for vertical elements (walls, columns, beams, etc). Care must be taken to also protect the top surface of the concrete appropriately</li> <li>“Breaking” or “Releasing” the formwork dramatically reduces the effectiveness of this curing method since air flow is now possible between the concrete and the formwork</li> <li>If uniform colour is an issue then a uniform curing time and temperature must also be maintained and form removal scheduled accordingly</li> </ul> </li> </ul>	<ul style="list-style-type: none"> <li>■ <b>Wet Burlap</b> <ul style="list-style-type: none"> <li>Pre-soaked burlap is applied to the concrete surface and is covered with plastic to prevent moisture loss or water is reapplied as necessary to prevent the material from drying out</li> <li>Burlap should be rinsed prior to its first use to avoid possible staining</li> <li>Materials utilizing both geotextile fabric and plastic top coatings can be reused throughout the project</li> </ul> </li> <li>■ <b>Wet Sand</b> <ul style="list-style-type: none"> <li>Wet loose material such as sand can be used to cure concrete slabs and footings</li> <li>The sand thickness must be sufficient to prevent moisture loss at the concrete surface or the sand must be wetted throughout the curing period</li> </ul> </li> </ul>

CSA A23.1 – TABLE 20

### Allowable curing regimes

(see Clause 4.1.1.1.1, 7.4.1.1, 7.4.1.7.1, and Table 2)

Curing Type	Name	Description
1	Basic	3 d at $\geq 10^{\circ}\text{C}$ or for a time necessary to attain 40% of the specified strength.
2	Additional	7 d at $\geq 10^{\circ}\text{C}$ and for a time necessary to attain 70% of the specified strength. When using silica fume concrete, additional curing procedures shall be used. See Annex I, Clause 1.3.13.
3	Extended	A wet-curing period of 7 d. The curing types allowed are ponding, continuous sprinkling, absorptive mat or fabric kept continuously wet.

References:

- |  |  |
|--|--|
| 1 CSA A23.1-04 – Concrete Materials and Methods of Concrete Construction, Canadian Standards Association International       | 3 Design and Control of Concrete Mixtures – 7th Canadian Edition, Cement Association of Canada   |
| 2 Ontario Building Code – 1997, Ontario Ministry of Municipal Affairs and Housing – Housing Development and Buildings Branch | 4 Concrete in Practice #11 – Curing In-Place Concrete, National Ready Mixed Concrete Association |

With permission of Canadian Standards Association, material is reproduced from CSA Standard, A23.1-04/A23.2-04, Concrete Materials and Methods of Concrete Construction/Methods of Test and Standard Practices for Concrete, which is copyrighted by Canadian Standards Association, 178 Rexdale Blvd., Toronto, Ontario, M9W 1R3. While the use of this material has been authorized, CSA shall not be responsible for the manner in which the information is presented, nor for any interpretations thereof. For more information on CSA or to purchase standards, please visit our website at [www.shopcsa.ca](http://www.shopcsa.ca) or call 1-800-463-6727.

This publication is intended for general information purposes only. The Ready Mixed Concrete Association of Ontario and the Cement Association of Canada disclaim any and all responsibility and liability for the accuracy and the application of the information contained in this publication to the full extent permitted by law.

No part of this publication may be reproduced in any form, including photocopying or other electronic means, without permission in writing from Ready Mixed Concrete Association of Ontario.

© 2005 RMCAO. All rights reserved. 09/05

Supported by



Cement Association of Canada  
Association Canadienne du Ciment

Technical information prepared by

**Ready Mixed Concrete Association of Ontario**  
365 Brunel Road, Unit #3 • Mississauga, Ontario L4Z 1Z5  
Tel: 905.507.1122 • Fax: 905.890.8122 • Email: [info@rmcao.org](mailto:info@rmcao.org)

[www.rmcao.org](http://www.rmcao.org)



**RMCAO**